

IN THE CLAIMS

Please amend the claims as follows:

- 1-11. (canceled)
12. (currently amended) Filter device for molten steel filtration comprising a bonded network of ~~graphitized~~graphitizable carbon, the filter device comprising a protruding frame joining a plurality of sieve plates, each plate including a corrugated surface, the protruding frame and sieve plates defining a reservoir chamber.
13. (previously presented) The filter device of claim 12, wherein at least one corrugated surface includes a surface corrugation from 0.1-10 mm.
14. (previously presented) The filter device of claim 13, wherein the surface corrugation is from 1-5 mm.
15. (previously presented) The filter device of claim 12, wherein each sieve plate defines a plurality of through holes, and the through holes of a first plate are spaced laterally from the through holes of a second plate.
16. (previously presented) The filter device of claim 15, wherein the through holes have a diameter from 1-10 mm.
17. (previously presented) The filter device of claim 16, wherein the through hole diameter is from 2-5 mm.
18. (previously presented) The filter device of claim 15, wherein the through holes comprise a shape selected from the group consisting of circular, elliptical, triangular, square, rectangular, pentagonal and hexagonal.
19. (previously presented) The filter device of claim 12, wherein the sieve plates include a substantially identical geometry.
20. (previously presented) The filter device of claim 12, wherein the filter comprises a ceramic raw material.
21. (previously presented) The filter device of claim 20, wherein the ceramic raw material includes reinforcing fiber.
22. (currently amended) A method for producing a filter device comprising a bonded network of ~~graphitized~~graphitizable carbon, the filter device comprising a protruding frame joining a

plurality of sieve plates, each plate including a corrugated surface, the protruding frame and sieve plates defining a reservoir chamber, the method comprising:

- a) pressing a semi-damp mixture comprising ceramic powder and a graphitizable bonding precursor and fibers to obtain a first and second perforated sieve plate, each plate having a disk shape, a protruding frame, and corrugated surface on at least one surface;
 - b) forming an assembly by joining the first and second perforated sieve plates by the protruding frames using a binder, whereby the plates and frame define a reservoir chamber;
 - c) firing the assembly in a non-oxidizing atmosphere to a temperature up to 1000°C.
23. (previously presented) The method of claim 22, wherein the binder is selected from a group consisting of ceramic or carbon.
24. (previously presented) The method of claim 22, wherein the non-oxidizing atmosphere is a reducing atmosphere.
25. (previously presented) The method of claim 22, wherein firing occurs between 600-700°C.
26. (previously presented) The method of claim 22, including roughening the corrugated surface.
27. (previously presented) The method of claim 22, wherein the semi-damp mixture includes a graphitizable carbon bonding precursor.
28. (previously presented) The method of claim 22, wherein the precursor is fired from 500-2000°C.